

Cardia Compostable B-MT02 (Flex)

Rigid Moulding Grade Resin

Biodegradable during Composting in Professionally Managed Facilities

Description

Cardia Compostable B-MT02 is a biodegradable and compostable resin based on a blend of thermoplastic starch (TPS), biodegradable polyesters and natural plasticizers. This grade of resin is compatibilised to offer a high level of mechanical strength, impact resistance and toughness. The resin is based on corn starch which is a renewable material.

- A biodegradable and compostable resin
- Designed to be used for injection moulding and profile/sheet extrusion

Specifications and Compliances

Cardia Compostable B-MT02 resin is biodegradable during composting in professionally managed composting facilities.

- Complies with International Standard ISO16929, ISO 14855
- Cardia Compostable B-MT02 complies with
 - European Standard EN13432,
 - USA Standard ASTM 6400,
 - Australian Standard AS 4736 and
 - Japanese “GreenPla” Standard
 - Chinese Environmental Labelling.

Application Examples

- Biodegradable injection moulded products such as cutlery, toothbrushes, combs, shavers, golf-tees, plant markers, etc.
- Extruded tubes and rods
- Biodegradable stakes and pegs
- Biodegradable tags
- Extruded pipes
- Injection moulded containers, caps and closures
- Compostable rigid products if wall thickness is kept below 1 mm.

Physical Properties of Cardia Compostable B-MT02

<i>Property</i>	<i>Test Method</i>	<i>Typical Value</i>	<i>Unit</i>
Melt Flow Index	ASTM D1238	8	g/10 min (190°C / 2.16 kg)
Density	ASTM D792	1.4	g/cm ³
Moisture Content	CBP method	<0.6	%
Tensile Strength at Break	ASTM D638	21	MPa
Elongation at Break	ASTM D638	1.6	%
Tensile Modulus (Elastic, Youngs)	ASTM D638	1340	MPa
Izod Impact - notched	ASTM D256	63	J/m

Transport, Storage and Handling

Cardia Bioplastics Materials should be transported, stored and handled in cool and dry environments without exposure to direct sunlight. More information can be retrieved from the Processing Guidelines available through your Cardia Bioplastics sales representative.

Safety

Material Safety Data Sheets (MSDS) are available. Please contact your Cardia Bioplastics sales representative.

Processing Conditions

Cardia Compostable™ B-MT02 materials can be easily processed on standard plastic process equipment. Processing guidelines are unique to this material and are available on request from the Cardia Bioplastics sales representative.

Disclaimer

This information is offered solely for your consideration and verification and should not be construed as a warranty of representation for which Cardia Bioplastics assumes legal liability, except to the extent that such liability is imposed by legislation and cannot be excluded. Values quoted are the results of tests on representative samples and the product supplied may not conform in all respects. Cardia Bioplastics reserves the right to make any improvements or amendments to the composition or any grade or product without alteration to the product code. In using Cardia Bioplastics products you must establish for yourself the most suitable formulation, production method and control tests to ensure the uniformity and quality of your product is in compliance with all laws.